

# Technical Data Sheet

13030 Black Acrylic Foam Tape

13030 Gray Acrylic Foam Tape

13030 White Acrylic Foam Tape

## Product Description

---

CCL Olympic 13030 is an ultra-thin, soft, acrylic foam tape with an aggressive tack that gives this tape its unique robust bonding performance. It is supplied between a durable polyester release liner and a polyethylene cover film, ensuring effortless handling and application.

In many applications, CCL Olympic 13030 can be used to replace mechanical fasteners such as rivets, screws, welds or liquid adhesives.


## Product Features

---

- High performance double sided pressure sensitive adhesive tape
- Unique visco-elastic nature ensures a strong bond which can absorb shocks and stress
- 0.3 mm thick
- Available in black (B), gray (G) or white (W).
- Long-lasting bond for indoor and outdoor applications
- The adhesives have an excellent solvent, plasticizer, and moisture resistance.
- Slitted on request
- 100% closed cell structure

## Product Construction

---



Technical Information Note: The technical data below cannot be used for specification purposes but should be considered representative or typical only.

#### Available sizes

| Property             | Value   | Additional information  |
|----------------------|---------|-------------------------|
| Standard roll length | 66 m.   | Other lengths available |
| Effective roll width | 900 mm. |                         |
| Core size            | 3 inch. | HIPS oversized          |

#### Typical Product Properties & Test Conditions

| Property             | Value                      | Method          | Additional information |
|----------------------|----------------------------|-----------------|------------------------|
| Total tape thickness | 0.3 mm.                    | ASTM D3652      |                        |
| Thickness tolerance  | 15%                        |                 |                        |
| Density              | 0.78 g/cm <sup>3</sup>     | Internal method |                        |
| Adhesive type        | Soft Acrylic               |                 |                        |
| Color                | Black, Gray or White       |                 |                        |
| Top liner            | 50 µm White Siliconized PE |                 |                        |
| Bottom liner         | 50 µm Transparent BoPET    |                 |                        |

## Typical Performance Characteristics

| Property                       | Value    | Method          | Additional information                |
|--------------------------------|----------|-----------------|---------------------------------------|
| 90° peel adhesion, initial     | 17 N/cm  | ASTM D3330      | Stainless Steel<br>20 min. dwell time |
| 90° peel adhesion, final       | 21 N/cm  | ASTM D3330      | Stainless Steel<br>72 hrs. dwell time |
| 90° peel adhesion, final       | 14 N/cm  | ASTM D3330      | PMMA<br>72 hrs. dwell time            |
| Static shear (20°C)            | 1500 G   | ASTM D3654      |                                       |
| Static shear (90°C)            | 500 G    | ASTM D3654      |                                       |
| Dynamic shear                  | 1375 kPa | ASTM D1002      | Shear rate: 12.7 mm/min               |
| Minimum long term temperature  | - 40 °C  | Internal Method |                                       |
| Maximum long term temperature  | 150 °C   | Internal Method |                                       |
| Maximum short term temperature | 200 °C   | Internal Method |                                       |

## Additional information test method

- 90° peel adhesion according to ASTM D3330. Stainless steel substrate, aluminum backing. 72-hour dwell time at room temperature. Listed value is average value force to remove adhesive at room temperature.
- Static shear according to ASTM D3654. Stainless steel substrates, 0.5 sq.in. (3.23 sq.cm.), 24-hour dwell time at room temperature. The adhesive will hold its listed weight for 10,000 minutes (approximately seven days) at the listed temperature.
- Long term maximum temperature is the temperature at which the adhesive will hold 250 grams under static load (10,000 minutes).
- Short term maximum temperature is the temperature to which the adhesive can be exposed for four hours with a static load of 100 grams.

## Product Applications

---

13030 is suitable for a range of applications including:


- Automotive wheel trims, mirrors and tread plates
- Outdoor signage and window grilles
- White goods
- Mobile electronics
- Component mounting

## Product code structure

---

The structure of our product code is as follows:

For example 13030G:



## Custom Solutions

---

We can modify all our adhesive and mechanical properties for various solutions, such as peel, adhesion, shear, softness, impact resistance, tack, color, rigidity, flexibility, temperature resistance and even smell to create the solution that meets your exact specifications.

## Additional Product Information

---

|                                 |  |
|---------------------------------|--|
| Product Application             | The application surface should be clean and dry. In order to optimize performance, surface temperatures should be around room temperature.   |
| Storage Conditions & Shelf Life | 13030 Olympic tapes must be stored between 10°C to 30°C, and 0-95% relative humidity. The optimum storage conditions are 22°C and 50% relative humidity and in original sealed packaging. If stored under recommended conditions, then this material will retain its specified performance criteria for 2 years. Performance of tapes is not projected to change even after shelf life expires, but it is recommended that the tapes be used within two years. |
| Conflict Minerals               | Conflict Minerals refers to illegal mining of minerals or other derivatives (Tin, Tantalum, Tungsten and Gold) mined in the provinces of the DRC (Democratic Republic of Congo). CCL-Olympic does not use Tin, Tantalum, Tungsten or Gold, or any derivative thereof, for the production of any of their products. Official statement available on request.  |
| RoHS                            | RoHS (Restriction of Hazardous Substances). Olympic hereby confirms that our products from series <b>LBL, 1000, 3000, 5000, 7000, 8000 and 9000</b> comply with EU Directive 2011/65/EU (RoHS recast/RoHS 2), as amended by EU 2015/863. Official statement available on request.  |
| REACH                           | Olympic hereby confirms that in case of products from the series <b>LBL, 1000, 3000, 5000, 7000, 8000 and 9000</b> we always observe the prescriptions of REACH (1907/2006/EC) regulation and the product(s) are fully compliant with the relevant regulation. Official statement available on request.  |
| PFAS                            | At CCL-Olympic, we want to reassure our customers that our products are entirely free of PFAS (Per- and Polyfluoroalkyl Substances), underscoring our commitment to product safety and environmental responsibility. Official statement available on request.  |
| ISO                             | CCL Olympic is ISO9001 and ISO14001 certified.   |

---

Warranty & Limited Liability Important Notice To Purchaser: All statements, technical information and recommendations herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties, expressed or implied, including the implied warranties, of merchantability and fitness for purpose: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT OR INDIRECT, INCIDENTAL, OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR THE INABILITY TO USE THE PRODUCT. No statement or recommendation not contained herein shall have any force or effect in an agreement signed by officers of seller or manufacturer.